



**Griffco Valve Inc.**  
6010 N. Bailey Ave., Suite 1B  
Amherst, NY 14226  
Phone: 1 716 835-0891  
Fax: 1 716 835-0893

## Technical Information

**Product: Back Pressure Valves  
Pressure Relief Valves**

**Release #: 2010-001**

**Application: Sulfuric Acid**

**Problem:** Griffco has noticed that over the past few years the feeding of sulfuric acid has become more problematic as the concentration of the product has exceeded 93%. The source of the failure is not poor material or the acid. In concentrations of 98.3% or higher, sulfuric acid had a natural contaminant known as sulfur trioxide (SO<sub>3</sub>). This has led to the new common terminology of 98+% sulfuric acid. This high concentration acid sulfuric attacks and causes stress fractures in both PVDF and Noryl. While PTFE is chemically compatible its cold flow properties make it difficult to seal at threaded connections. Alloy 20 is a bullet proof solution, but is extremely expensive.

**Solution:** Griffco is committed to supplying valves for this application that will be chemically compatible and will not leak. The following will outline our offerings for sulfuric acid, noting the limits each will have.

- 1) Noryl – for concentrations to 95% and 200° F
- 2) PVDF – for concentrations to 95% and 175° F
- 3) Halar – for concentrations to 100% and 200° F
- 4) PTFE (flanged one piece construction) – for concentrations to 100% and 200° F
- 5) Alloy 20 - for concentrations to 100% and 300° F

**Note:** Although the information presented herein is presented in good faith and believed to be correct, Griffco Valve Inc., makes no guarantee or representation as to the completeness or accuracy thereof, and disclaims all liability for loss or damage resulting from use or reliance upon any information, recommendations or suggestions contained herein. Any selection made is at the responsibility of the end user.